

LNP™ STAT-KON™ COMPOUND 9X08403C

9X08403C

REGION AMERICAS

DESCRIPTION

LNP STAT-KON 9X08403C is a compound based on Liquid Crystal Polymer (LCP) resin containing Carbon Fiber. Added features of this material are: Clean Compounding System, High Temperature, Flame Retardant, Electrically Conductive, Good barrier against water and oxygen.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	153	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.7	%	ASTM D 638
Tensile Modulus, 5 mm/min	14800	MPa	ASTM D 638
Flexural Stress	53	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	14400	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	826	J/m	ASTM D 4812
Izod Impact, notched, 23°C	87	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	280	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.46	-	ASTM D 792
Density	1.46	g/cm ³	ASTM D 792
Mold Shrinkage, flow (5)	0.2	%	SABIC method
Mold Shrinkage, xflow (5)	0.52	%	SABIC method
ELECTRICAL			
Volume Resistivity	100000 – 1000000000	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+05 – 1.E+09	Ohm	ASTM D 257
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	1 – 3	hrs	
Maximum Moisture Content	0.01	%	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	330 – 360	°C	
Nozzle Temperature	330 – 360	°C	
Front - Zone 3 Temperature	330 – 360	°C	
Middle - Zone 2 Temperature	330 – 360	°C	
Rear - Zone 1 Temperature	325 – 360	°C	
Mold Temperature	65 – 110	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.