

Cycloloy* Resin CX5430

Americas: COMMERCIAL

Cycloloy* resin CX5430 is a general purpose PC/ABS blend developed for thin wall applications requiring weld line strength, high flow and impact together with a good balance of other properties.

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Tensile Stress, yld, Type I, 50 mm/min	50	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	45	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	>50	%	ASTM D 638
Tensile Modulus, 5 mm/min	2400	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	75	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D 790
Taber Abrasion, CS-17, 1 kg	70	mg/1000cy	SABIC Method
Tensile Stress, yield, 5 mm/min	44	MPa	ISO 527
Tensile Stress, break, 5 mm/min	44	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	48	MPa	ISO 527
Tensile Stress, break, 50 mm/min	44	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5	%	ISO 527
Tensile Strain, break, 5 mm/min	>50	%	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	>50	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	75	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
Hardness, Rockwell L	90	-	ISO 2039-2
Hardness, Rockwell R	115	-	ISO 2039-2
IMPACT	Value	Unit	Standard
Izod Impact, notched, 23°C	500	J/m	ASTM D 256
Izod Impact, notched, -30°C	250	J/m	ASTM D 256
Izod Impact, double-gated, 23°C	110	J/m	SABIC Method
Multiaxial Impact	80	J	ISO 6603
Instrumented Impact Total Energy, 23°C	55	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	40	J	ASTM D 3763
Izod Impact, notched 80*10*3 +23°C	40	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	20	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	40	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	20	kJ/m ²	ISO 179/1eA
THERMAL	Value	Unit	Standard
Vicat Softening Temp, Rate B/50	115	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	115	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	95	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ASTM E 831

Thermal Conductivity	0.2	W/m-°C	ASTM C 177
Thermal Conductivity	0.2	W/m-°C	ISO 8302
CTE, -40°C to 40°C, flow	8.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	pass	-	IEC 60695-10-2
Ball Pressure Test, approximate maximum	100	°C	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	114	°C	ISO 306
Vicat Softening Temp, Rate B/120	115	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	117	°C	ISO 75/Be
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	95	°C	ISO 75/Af
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL	Value	Unit	Standard
Specific Gravity	1.15	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 - 0.7	%	SABIC Method
Melt Flow Rate, 260°C/5.0 kgf	19	g/10 min	ASTM D 1238
Density	1.15	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.3	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Density (Molded)	1.15	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 260°C/5.0 kg	18	cm ³ /10 min	ISO 1133
ELECTRICAL	Value	Unit	Standard
Volume Resistivity	> 1.E+15	Ohm-cm	ASTM D 257
Surface Resistivity	> 1.E+15	Ohm	ASTM D 257
Dielectric Strength, in oil, 0.8 mm	35	kV/mm	IEC 60243-1
Dielectric Strength in oil, 1.5mm	25	kV/mm	IEC 60243-1
Relative Permittivity, 50/60 Hz	2.9	-	IEC 60250
Relative Permittivity, 1 kHz	2.7	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.01	-	IEC 60250
Dissipation Factor, 1 MHz	0.011	-	IEC 60250
FLAME CHARACTERISTICS	Value	Unit	Standard
UL Recognized, 94HB Flame Class Rating (3)	1.5	mm	UL 94
UL Recognized, 94HB Flame Class Rating 2nd value (3)	3	mm	UL 94
Glow Wire Flammability Index 650°C, passes at	3.2	mm	IEC 60695-2-12

Source GMD, last updated:09/05/2006

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	100 - 110	°C
Drying Time	2 - 4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	260 - 290	°C
Nozzle Temperature	240 - 280	°C
Front - Zone 3 Temperature	250 - 290	°C
Middle - Zone 2 Temperature	250 - 290	°C
Rear - Zone 1 Temperature	230 - 260	°C
Hopper Temperature	60 - 80	°C
Mold Temperature	60 - 90	°C

Source GMD, last updated:09/05/2006

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

- (1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.
- (2) Only typical data for selection purposes. Not to be used for part or tool design.
- (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
- (4) Internal measurements according to UL standards.

Disclaimer : THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

* Cycoloy is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company. All rights reserved