

LEXANT™ COPOLYMER SLX2571T

REGION AMERICAS

DESCRIPTION

Transparent weatherable PC copolymer for blowmolding/extrusion.

TYPICAL PROPERTY VALUES

Revision 20240719

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	64	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	7.5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	106	%	ASTM D638
Tensile Modulus, 5 mm/min	2400	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	101	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2400	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	63	MPa	ISO 527
Tensile Stress, break, 50 mm/min	63	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	98	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	94	MPa	ISO 178
Flexural Modulus, 2 mm/min	2240	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	848	J/m	ASTM D256
Izod Impact, notched, -30°C	141	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	74	J	ASTM D3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	70	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	75	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	15	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
Vicat Softening Temp, Rate B/50	143	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	126	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.02E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.36E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	6.02E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.36E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	143	°C	ISO 306
Vicat Softening Temp, Rate B/120	145	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	125	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Specific Gravity	1.2	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.6 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	3	g/10 min	ASTM D1238
Density	1.2	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	2	cm ³ /10 min	ISO 1133
EXTRUSION BLOW MOLDING ⁽³⁾			
Drying Temperature	115 – 120	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Minimum Moisture Content	0.01	%	
Melt Temperature (Parison)	265 – 275	°C	
Barrel - Zone 1 Temperature	260 – 275	°C	
Barrel - Zone 2 Temperature	260 – 275	°C	
Barrel - Zone 3 Temperature	260 – 275	°C	
Barrel - Zone 4 Temperature	260 – 275	°C	
Adapter - Zone 5 Temperature	260 – 275	°C	
Head - Zone 6 - Top Temperature	260 – 275	°C	
Head - Zone 7 - Bottom Temperature	260 – 275	°C	
Screw Speed	15 – 50	rpm	
Mold Temperature	65 – 95	°C	
Die Temperature	270 – 280	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(3) Processing parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.